

**SEC 24" X 24" ECO GREEN ENVIRONMENT FRIENDLY NYLON CARPET:  
SPECIFICATIONS:**

|                             |   |
|-----------------------------|---|
| Minimum Sq. Yd.             | <b>No minimum</b>   |
| Construction                | <b>Tufted</b>   |
| Surface Texture             | <b>Level Patterned Loop</b>   |
| Gauge                       | <b>1/12 (49.00 rows per 10 cm)</b>  |
| Density                     | <b>7200</b>   |
| Weight Density              | <b>122,400</b>  |
| Sustainable Content         | <b>Contains a minimum 35% pre-consumer recycled content by total weight</b>       |
| Stitches Per Inch           | <b>10.3 (40.55 per 10 cm)</b>   |
| Finished Pile Thickness     | <b>.085" (2.16 mm)</b>  |
| Dye Method                  | <b>Solution Dyed</b>  |
| Backing Material            | <b>EcoFlex ICT</b>  |
| Fiber Type                  | <b>Colorstrand® SD Nylon</b>  |
| Face Weight                 | <b>17.0 oz. per sq. yd. (576 g/m2)</b>  |
| Pattern Repeat              | <b>Not Applicable</b>   |
| Size/Width                  | <b>24" x 24" (.6096 m x .6096 m)</b>  |
| Soil Release Technology     | <b>Sentry Plus</b>  |
| Installation Method         | <b>Monolithic, Vertical Ashlar, Quarter Turn, Brick Ashlar, Multi-Directional</b> |
| Indoor Air Quality          | <a href="#"><u>Green Label Plus 1098</u></a>                                      |
| Foot Traffic Recommendation | <b>Heavy</b>  |
| TARR                        |   |
| NSF 140                     | <b>Gold (Platinum option available)</b>   |
| PERFORMANCE                 |   |
| Static                      | <b>AATCC-134 Under 3.5 KV</b>   |
| Flammability                | <b>ASTM E 648 Class 1 (Glue Down)</b>   |
| Smoke Density               | <b>ASTM E 662 Less than 450</b>   |
| others                      | <a href="#"><u>Colorfastness to Light &amp; Atmospheric Contaminants</u></a>      |

*"Color may vary from dye lot to dye lot. Substitution of material may be made due to improved technology, supply limitations, or other factors. The performance is not affected by such variances. All Specifications are subject to normal manufacturing tolerances."*